

ALLEN® 2055MT

Co-extruded, Medium Impact ABS, Matte Gloss Sheet

INTRODUCTION

ALLEN® 2055MT is a general purpose ABS with medium impact strength and a matte gloss finish.

GENERAL INFORMATION

ALLEN® 2055MT has been tested under laboratory conditions and meets the requirements of Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302).

SUGGESTED APPLICATIONS

- Covers and Housings
- Motor Vehicle Interior dashboards, panels, trim, headliners and B pillars
- RV Interiors
- Heavy Truck Interiors
- Construction Vehicle Interiors
- Displays
- Fork Lift Trucks
- Agricultural Equipment Interiors

FEATURES

- Custom color matching
- Good forming properties
- Edge trim easily used in future orders
- Matte Gloss

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: www.kydex.com.



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305, +1.616.694.3808
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

ALLEN® 2055MT

Co-extruded, Medium Impact ABS, Matte Gloss Sheet

PROPERTY	TEST METHOD	TYPICAL VALUE ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.05 g/cc	
Gloss, 60° Angle	ASTM D523	<15%	
MECHANICAL			
Tensile Strength, yield	ASTM D638	34.4 MPa	5,000 psi
Flexural Stress at 5% Strain	ASTM D790	55.1 MPa	8,000 psi
Flexural Modulus	ASTM D790	1,930.5 MPa	280,000 psi
Notched Izod Impact Resistance, 73°F	ASTM D256	213 J/m	4.0 ft-lbs/in
Notched Izod Impact Resistance, 0°F	ASTM D256	106 J/m	2.0 ft-lbs/in
THERMAL			
Heat Deflection Temperature (HDT) 66 psi (0.45 MPa), Unannealed	ASTM D648	90.5°C	195°F
Mold Shrinkage	ASTM D955	0.005 - 0.007 in/in	
FLAMMABILITY			
Motor Vehicle Safety Standard	Component Recognition	Pass	
¹ Values based upon injection molded resin. Not intended for specification purposes.			



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
 Phone: 800.823.1305, +1.616.694.3808
 Email: info@kydex.com

appLab™

Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.