

ALLEN® 5060WLG

Co-extruded, High Impact ASA/ABS, Low to Medium Gloss Sheet

INTRODUCTION

ALLEN® 5060WLG is high impact ABS capped with ASA for UV protection and low to medium gloss finish.

GENERAL INFORMATION

ALLEN® 5060WLG has been tested under laboratory conditions and has achieved a UL94 HB rating at 0.060 in (1.52mm) and above and meets the requirements of Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302).

SUGGESTED APPLICATIONS

- Vehicle Exteriors
- Marine Parts
- Radomes
- Agriculture Equipment Exteriors
- Construction Equipment Exteriors
- Lift Boom Exteriors

FEATURES

- Custom color matching
- Excellent UV properties
- Edge trim easily used into future orders
- Low to medium gloss finish
- Color and gloss retention

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: www.kydex.com.



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305, +1.616.694.3808
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

ALLEN® 5060WLG

Co-extruded, High Impact ASA/ABS, Low to Medium Gloss Sheet

PROPERTY	TEST METHOD	TYPICAL VALUE ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.03	
Density	ASTM D792	1.03 g/cm ³	0.037 lb/in ³
Water Absorption, equilibrium, 73°F	ASTM D570	0.27%	
Rockwell Hardness, R-scale	ASTM D785	93	
MECHANICAL			
Tensile Strength	ASTM D638	42.0 MPa	6,090 psi
Tensile Modulus	ASTM D638	1909.8 MPa	277,000 psi
Flexural Stress at 5% Strain	ASTM D790	63.4 MPa	9,190 psi
Flexural Modulus	ASTM D790	1985.7 MPa	288,000 psi
Compressive Strength, yield	ASTM D695	47.5 MPa	6,890 psi
Shear Strength	ASTM D732	39.2 MPa	5,690 psi
Bearing Strength, 4% deflection	ASTM D953	20.3 MPa	2,940 psi
Bearing Strength, max.	ASTM D953	177.2 MPa	25,700 psi
Notched Izod Impact Resistance	ASTM D256	283.5 J/m	5.3 ft-lb/in
Notched Izod Impact Resistance @ -20°F (-29°C)	ASTM D256	165.5 J/m	3.1 ft-lb/in
Gardner Drop Dart Impact, GE	ASTM D5420	46.1 J	408 in-lb _f
Gardner Drop Dart Impact, GE @ -20°F (-29°C)	ASTM D5420	24.7 J	219 in-lb _f
THERMAL			
Heat Deflection Temperature (HDT) 264 psi (1.8 MPa), Annealed	ASTM D648	91.0°C	195.8°F
Heat Deflection Temperature (HDT) 66 psi (0.45 MPa), Annealed	ASTM D648	96.2°C	205.2°F
Coefficient of Thermal Expansion (TD)	ASTM E831	97.7 µm/m/°C	54.3 µin/in/°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	20.4 kV/mm	517 V/mil
FLAMMABILITY²			
Underwriters Laboratories, Inc.® Component Recognition	UL Standard 94 ²	HB @ 0.060 in (1.52mm)	
Motor Vehicle Safety Standard	FMVSS 302	Passes	
¹ Values based upon 0.125" (3.17mm) sheet unless otherwise specified. ² ALLEN® 5060WLG has been tested under laboratory conditions and has passed UL 94HB criteria. SEKISUI KYDEX, LLC makes no warranty or guarantee that these products will meet UL 94HB in the part's final, finished configuration. Not intended for specification purposes.			



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
 Phone: 800.823.1305, +1.616.694.3808
 Email: info@kydex.com

appLab™

Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.