

## ALLEN® 8050TX

High impact, fire rated PC/ABS, high gloss sheet

### INTRODUCTION

ALLEN® 8050TX is a general purpose PC/ABS with high impact strength and high heat deflection.

### GENERAL INFORMATION

ALLEN® 8050TX meets Federal Motor Vehicle Safety Standard No. 302 (FMVSS302).

### SUGGESTED APPLICATIONS

- Vehicle Interior Trim
- Covers and Housings
- Fan Shrouds
- Vehicle Exteriors (painted)
- Instrument Panels

### FEATURES

- Custom color matching
- Good forming properties
- Edge trim easily used for future orders
- High heat deflection temperature
- High gloss finish
- Meets many automotive specifications

### ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: [www.kydex.com](http://www.kydex.com).



#### Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA  
Phone: 800.823.1305, +1.616.694.3808  
Email: [info@kydex.com](mailto:info@kydex.com)

#### appLab™

Phone: 800.682.8758  
Email: [applab@kydex.com](mailto:applab@kydex.com)

[kydex.com](http://kydex.com)

## ALLEN® 8050TX

High impact, fire rated PC/ABS, high gloss sheet

Property	Test Method	Typical Value <sup>1</sup>	
<b>PHYSICAL</b>			
Specific Gravity	ASTM D792	1.14	
Water Absorption, 24hr	ASTM D570	0.17 %	
Rockwell Hardness, R-Scale	ASTM D785	117	
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	8,520 psi	58.7 MPa
Tensile Modulus	ASTM D638	358,000 psi	2,468 MPa
Flexural Modulus	ASTM D790	374,000 psi	2,579 MPa
Flexural Stress at 5% Strain	ASTM D790	13,700 psi	94.5 MPa
Compressive Strength, yield	ASTM D695	10,800 psi	74.5 MPa
Shear Strength	ASTM D732	8,860 psi	61.1 MPa
Bearing Strength, 4% deflection	ASTM D953	3,820 psi	26.3 MPa
Bearing Strength, max.	ASTM D953	36,100 psi	248.9 MPa
Notched Izod Impact Resistance	ASTM D256	10.4 ft-lbs/in	555.2 J/m
Notched Izod Impact Resistance	ASTM D256	8.2 ft-lbs/in	437.8 J/m
Gardner Drop Dart Impact, GE	ASTM D5420	632 in-lbf	71.4 J
<b>THERMAL</b>			
Heat Deflection Temperature (HDT) @264 psi (1.8 MPa), unannealed	ASTM D648	252 °F	122 °C
Heat Deflection Temperature (HDT) @66 psi (0.45 MPa), unannealed	ASTM D648	266 °F	130 °C
Coefficient of Thermal Expansion (MD)	ASTM E831	36.5 µin/in/°F	65.6 µm/m/°C
<b>ELECTRICAL</b>			
Dielectric Strength, oil	ASTM D149	481 V/mil	18.9 kV/mm
<b>FLAMMABILITY</b>			
Motor Vehicle Safety Standard	FMVSS 302	PASS	
<sup>1</sup> Values based upon 0.125" (3.17mm) sheet unless otherwise specified. Not intended for specification purposes.			



### Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA  
 Phone: 800.823.1305, +1.616.694.3808  
 Email: info@kydex.com

### appLab™

Phone: 800.682.8758  
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.