

ALLEN® 8150SM

High impact, high HDT PC/ABS, high gloss sheet

INTRODUCTION

ALLEN® 8150SM is a general purpose PC/ABS with high impact strength and high heat deflection.

GENERAL INFORMATION

ALLEN® 8150SM meets the requirements of Federal Motor Vehicle Safety Standard No. 302 (FMVSS 302).

SUGGESTED APPLICATIONS

- Vehicle Interior Trim
- Covers and Housings
- Vehicle Exteriors (painted)
- Instrument Panels

FEATURES

- Custom color matching
- Good forming properties
- Edge trim easily used for future orders
- High heat deflection temperature
- High gloss finish
- Meets many automotive specification

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: www.kydex.com.



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305, +1.616.694.3808
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

ALLEN® 8150SM

High impact, high HDT PC/ABS, high gloss sheet

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.13	
Water Absorption, 24hr	ASTM D570	0.17%	
Rockwell Hardness, R-Scale	ASTM D785	111	
MECHANICAL			
Tensile Strength	ASTM D638	6,960 psi	48.0 MPa
Tensile Modulus	ASTM D638	304,000 psi	2096.0 MPa
Flexural Modulus	ASTM D790	323,000 psi	2227.0 MPa
Flexural Stress at 5% Strain	ASTM D790	11,600 psi	80.0 MPa
Compressive Strength, yield	ASTM D695	8,590 psi	59.2 MPa
Shear Strength	ASTM D732	7,830 psi	54.0 MPa
Bearing Strength, 4% deflection	ASTM D953	4,040 psi	27.9 MPa
Bearing Strength, max.	ASTM D953	33,100 psi	228.2 MPa
Notched Izod Impact Resistance	ASTM D256	9.81 ft-lbs/in	523.9 J/m
Gardner Drop Dart Impact, GE	ASTM D5420	443 in-lbf	50.1 J
THERMAL			
Heat Deflection Temperature (HDT) @264 psi (1.8 MPa), unannealed	ASTM D648	244.4 °F	118 °C
Heat Deflection Temperature (HDT) @66 psi (0.45 MPa), unannealed	ASTM D648	264.2 °F	129 °C
Coefficient of Thermal Expansion (MD)	ASTM E831	42.8 µin/in/°F	77 µm/m/°C
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	552 V/mil	21.7 kV/mm
FLAMMABILITY²			
Motor Vehicle Safety Standard	FMVSS 302	PASS	

¹ Values based upon 0.125" (3.17mm) sheet unless otherwise specified.

² All thicknesses

Not intended for specification purposes.



Customer Collaboration

1305 Lincoln Ave. Holland MI 49423 USA
Phone: 800.823.1305, +1.616.694.3808
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.