

KYDEX® 6523HI

High impact, integral pearlescent aviation sheet

INTRODUCTION

KYDEX® 6523HI is a proprietary, high performance thermoplastic sheet with integral colour specifically engineered to improve aircraft passenger safety. Integrally pearlescent, this sheet is perfect to use with LED lighting or on its own.

GENERAL INFORMATION

KYDEX® 6523HI is designed to provide material deformation when used in components subjected to the HIC (Head Injury Criterion) Test for increased passenger safety. Its integral pearlescent colour gives the appearance of painted metal and allows light weighting and increased durability when replacing composite and metal panels. It meets the flammability and smoke development requirements outlined in FAR 25.853(a) and (d).

SUGGESTED APPLICATIONS

- Seat parts
- Bulkhead laminates
- Life vest shrouds
- Passenger service units
- Monitor Shrouds
- Armrests
- Moulding strips
- Tray tables
- Kick panels

FEATURES

- Improved impact properties over traditional thermoplastics for HIC compliance seating requirements
- Meets the stringent requirements of FAR 25.853(d) in all thicknesses and colours
- Excellent formability and fabrication characteristics
- Allows for tight tolerance control
- Increases design freedom to create more complex seat geometries
- Available in a wide range of integral colours
- Available in P3 - Velour Matte

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health, and environmental protection. We support the safe handling of our products.

Please contact our appLab™ department at 800.682.8758 for resources and Safety Data Sheets or visit our website: www.kydex.com.



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™

Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

KYDEX® 6523HI

High impact, integral pearlescent aviation sheet

Property	Test Method	Typical Value ¹	
PHYSICAL			
Specific Gravity	ASTM D-792	1.46	
Water Absorption, 24 hr	ASTM D-570	0.05%	
Rockwell Hardness, R-Scale	ASTM D-785	104	
MECHANICAL			
Tensile Strength	ASTM D-638	38.3 MPa	5,560 psi
Tensile Modulus	ASTM D-638	3,558 MPa	516,000 psi
Poisson's Ratio	ASTM D-638	0.382	
Flexural Strength	ASTM D-790	67.7 MPa	9,820 psi
Flexural Modulus	ASTM D-790	3,420 MPa	496,000 psi
Compressive Strength, yield	ASTM D-695	56.1 MPa	8,130 psi
Compressive Modulus	ASTM D-695	3,116 MPa	452,000 psi
Shear Strength	ASTM D-732	38.6 MPa	5,600 psi
Bearing Strength, 4% deflection	ASTM D-953	33.4 MPa	4,840 psi
Bearing Strength, max	ASTM D-953	204.8 MPa	29,700 psi
Gardner Drop Dart Impact, GE geometry	ASTM D-5420	51.5 J	456 in-lb _f
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D-648	79.1°C	174°F
Coefficient of Thermal Expansion	ASTM E-831	58.6 µm/m/°C	32.5 µin/in/°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D-149	> 24.8 kV/mm	> 630 V/mil
FLAMMABILITY²			
Vertical Burn, 60-second	FAR 25.853(a) Part 1 (a)(i)	Pass	
Vertical Burn, 12-second	FAR 25.853(a) Part 1 (a)(ii)	Pass	
OSU Heat Release	FAR 25.853(d) Part IV	Pass	
NBS Smoke Density	FAR 25.853(d) Part V	Pass	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² All thicknesses and colours Not intended for specification purposes.			



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Email: info@kydex.com

applab™

Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.