

KYDEX® T

High Impact Fire-Rated Sheet

INTRODUCTION

KYDEX® T is a proprietary thermoplastic sheet that is cost competitive with fire retardant ABS/PVC (FR-ABS) formulations but with significantly higher impact strength and extensibility.

GENERAL INFORMATION

Since KYDEX® T is less hygroscopic, unlike FR-ABS, it typically does not require pre-drying, offers superior impact, more uniform forming with less wall thinning and offers significantly greater resistance to a broad range of corrosive chemicals and cleaning solutions. It is available in a wide range of aesthetic choices and is Underwriter's Laboratories, Inc® recognized Std 94 V-0, 5V.

SUGGESTED APPLICATIONS

- Aircraft Interiors
- Equipment Housings
- Kiosk Housings
- Mass Transit Vehicle Interior Components
- Medical Products

FEATURES

- Substitute for FR-ABS sheet with competitive pricing but superior cost/performance
- Higher breakage resistance measured by the Notched Izod test than competitive thermoplastics
- Available in thicknesses from 0.71mm (0.028") and up, in eight textures, a variety of colors, custom blank sizes and low minimums
- Among the most rigid of thermoforming materials with a modulus of elasticity of 2,482 MPa (360,000 psi)
- Easy to form with excellent part definition and deep-draw characteristics
- Recognized by Underwriter's Laboratories, Inc® for Std 94 V-0, 5V in all thicknesses
- Form times similar to FR-ABS making it an easy transition from competitive products.

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.kydex.com>. For Material Safety Data Sheets, please call 800.325.3133.



Customer Collaboration
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™
Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

KYDEX® T High Impact Fire-Rated Sheet

PROPERTY	TEST METHOD	TYPICAL VALUE ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.35	
Rockwell Hardness, R-scale	ASTM D785	94	
Moisture Absorption, 24 hrs. @ 50°C	ASTM D570	0.08%	
MECHANICAL			
Tensile Strength	ASTM D638	42 MPa	6,100 psi
Tensile Modulus	ASTM D638	2,600 MPa	382,000 psi
Poisson's Ratio	ASTM D638	0.433	
Elongation	ASTM D638	110%	
Flexural Strength	ASTM D790	66 MPa	9,600 psi
Flexural Modulus	ASTM D790	2,480 MPa	360,000 psi
Izod Impact, notched	ASTM D256	801 J/m	15 ft-lb _f /in
Compressive Strength, yield	ASTM D695	54 MPa	7,900 psi
Compressive Modulus	ASTM D695	3,300 MPa	489,000 psi
Shear Strength	ASTM D732	50 MPa	7,380 psi
Bearing Strength, 4% deflection	ASTM D953	31 MPa	4,600 psi
Bearing Strength, Max	ASTM D953	197 MPa	28,700 psi
Gardner Drop Dart Impact, GE	ASTM D5420	>70 J	>627 in-lb _f
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D648	75.6°C	168°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D149	17.1 kV/mm	435 V/mil
FLAMMABILITY			
Underwriters Laboratories, Inc.® Component Recognition	UL Standard 94 ²	V-0, 5V ³	
Vertical Burn, 60-second	FAR 25.853(a)(i)	Pass	
Vertical Burn, 12-second	FAR 25.853(a)(ii)	Pass	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² Underwriters Laboratories, Inc.®, File Number E115252 ³ All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			



Customer Collaboration
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Email: info@kydex.com

appLab™
Phone: 800.682.8758
Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.