

# Radiation Effects on KYDEX® Thermoplastic Sheet

## GENERAL INFORMATION

KYDEX® sheet was irradiated using Cobalt-60 (gamma energies 1.173 MeV, 1.331 MeV) to the total dose listed below. Color and impact properties are not negatively affected for doses up to 3.50 E<sup>6</sup> rads.

Dose Rate: 1.406 E<sup>6</sup> Rads/hr average

Total Dose: 3.52 E<sup>6</sup> or 3.52 E<sup>7</sup> Rads

Dose Measurement: Keithley Autoranging Picoammeter Model 485 with LND Ionization Chamber Probe.

Product	Total Dose	Izod Impact	ΔL	Δa	Δb	ΔE
KYDEX® T	0	15.36	--	--	--	--
KYDEX® T	3.5 E <sup>6</sup>	16.18	-0.27	-0.08	0.71	0.77
KYDEX® T	35.0 E <sup>6</sup>	14.71	-0.60	0.84	7.45	9.66
KYDEX® 100	0	17.62	--	--	--	--
KYDEX® 100	3.5 E <sup>6</sup>	19.18	-0.20	-0.07	0.41	0.46
KYDEX® 100	35.0 E <sup>6</sup>	16.88	-5.07	-1.05	6.23	8.51



### Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA  
 Phone: 800.325.3133, +1.570.389.5810  
 Email: info@kydex.com

### appLab™

Phone: 800.682.8758  
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.