

KYDEX® 4545

Ultra low heat release and smoke density aviation sheet

INTRODUCTION

KYDEX® 4545 is a proprietary, high performance thermoplastic sheet specifically formulated to exceed the heat release and smoke density requirements in FAR 25.853 making it an ideal material for composite constructions.

GENERAL INFORMATION

KYDEX® 4545 exceeds the flammability and smoke development requirements outlined in Federal Aviation Regulations (FAR) 25.853 paragraphs (a) and (d). Its low heat release and smoke density offers an enhanced level of safety for interior components while making it an ideal material for composite constructions. Its wide processing window and ease of thermoforming makes it perfect for complex parts.

SUGGESTED APPLICATIONS

- Seat parts
- Armrests
- Bulkhead laminates
- Moulding strips
- Passenger service units
- Tray tables
- Monitor shrouds
- Kick panels

FEATURES

- Exceeds the stringent requirements of FAR 25.853(d) in all thicknesses and colors
- Excellent formability and fabrication characteristics
- Processes similar to KYDEX® 6565 and KYDEX® 5555
- Allows for tight tolerance control
- Available in a wide range of colors
- Available in P3 – Velour Matte texture

ENVIRONMENTAL & SAFETY CONSIDERATIONS

SEKISUI KYDEX, LLC is committed to ensuring that its products can be manufactured, transported, stored, used, disposed and recycled with an appropriate regard for safety, health and environmental protection. We support the safe handling of our products. Please contact our Technical Service department at 800.682.8758 for resources or visit our website: <http://www.kydex.com>. For Material Safety Data Sheets, please call 800.325.3133.



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA

Phone: 800.325.3133, +1.570.389.5810

Email: info@kydex.com

appLab™

Phone: 800.682.8758

Email: applab@kydex.com

kydex.com

KYDEX® 4545

Ultra low heat release and smoke density aviation sheet

PROPERTY	TEST METHOD	TYPICAL VALUE ¹	
PHYSICAL			
Specific Gravity	ASTM D792	1.49	
Water Absorption, 24hr	ASTM D-570	0.07%	
Rockwell Hardness, R-scale	ASTM D785	113	
MECHANICAL			
Tensile Strength	ASTM D-638	54.8 MPa	7,950 psi
Tensile Modulus	ASTM D-638	3,689 MPa	535,000 psi
Poisson's Ratio	ASTM D-638	0.38	
Flexural Strength	ASTM D-790	87.6 MPa	12,700 psi
Flexural Modulus	ASTM D-790	3,605 MPa	523,000 psi
Compressive Strength, yield	ASTM D-695	68.3 MPa	9,900 psi
Compressive Modulus	ASTM D-695	3,785 MPa	549,000 psi
Shear Strength	ASTM D-732	52.4 MPa	7,600 psi
Bearing Strength, 4% deflection	ASTM D-953	39.5 MPa	5,730 psi
Bearing Strength, max.	ASTM D-953	253.7 MPa	36,800 psi
THERMAL			
Heat Deflection Temperature (HDT) @ 264 psi (1.8 MPa) annealed	ASTM D648	75.3°C	168°F
Coefficient of Thermal Expansion	ASTM E-831	56.9 µm/m/°C	31.6 µin/in/°F
ELECTRICAL			
Dielectric Strength, oil	ASTM D-149	>18.7 kV/mm	>475 V/mil
FLAMMABILITY²			
Vertical Burn, 60-second	FAR 25.853(a)(i)	Pass	
Vertical Burn, 12-second	FAR 25.853(a)(ii)	Pass	
NBS Smoke Density	FAR 25.853(d) Part V	D _g max <150	
OSU Heat Release	FAR 25.853(d) Part IV	Total: <45 kW-min/m ² Peak: <45 kW/m ²	
¹ Values based upon 3.18mm (0.125") sheet unless otherwise specified. ² All thicknesses 0.71mm (0.028") and above Not intended for specification purposes.			



Customer Collaboration
 6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Email: info@kydex.com

applab™
 Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. The products discussed are sold without warranty of merchantability or fitness for a particular use, either expressed or implied, except as provided in our standard terms and conditions of sale. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.