

KYDEX® 3D Laminates

For membrane pressed and flat lamination applications
TB - 100-B

Introduction

KYDEX® 3D thermoplastic laminates give designers the ability to incorporate compound corners and contoured edges, logos, and wire management holes while eliminating unsightly seams and the need for edge banding typically associated with HPL/TFM surfaces. Its high impact resistance minimizes costly maintenance associated with other membrane pressed and flat laminates. Available in Extreme Durability (XD), Extreme Durability with antimicrobial product protection (XD MB), and Wood Grain (XDWG) product grades.

Where to use KYDEX® 3D Laminates

- Store fixtures
- Checkout counters
- Exhibits and displays
- Moldings
- Transaction surfaces
- Tabletops
- Flat laminated panels
- Kiosks
- Cabinetry
- Door and drawer fascias
- Pedestals and stands
- Workstations
- Logo and trademark panels

Which KYDEX® 3D Laminate to choose


KYDEX® 3D Laminate product grade comparison:

KYDEX® XD	KYDEX® XDWG
Extreme durability surface coverage	Available in 12 stocked wood grains
Low minimum order quantities for custom colours	Substrate colour matched to wood grain
Deep draws due to high extensibility	Can be sold by the sheet
Available in multiple textures.	All designs have matching vinyl film as well as HPL or TFM

Why use KYDEX® 3D Laminates

KYDEX® 3D Laminates compared with HPL:

HPL	KYDEX® XD
Fractures and Chips	Resists Gouges / Extreme Durability
Unable to form to curved surfaces and complex shapes requiring seams	Able to seamlessly form to complex shapes and draw over deep recesses
Loses colour integrity even with shallow scratches	Integral colour reduces visibility of surface scratches



SEKISUI SPI
ISO 9001 and 14001 Certified

Customer Service
6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@sekisui-spi.com

Technical Service
Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

KYDEX® 3D Laminates

For membrane pressed and flat lamination applications
TB - 100-B

Membrane Pressing Conditions

Average Membrane Pressing Processing Conditions:

	Pre-Blowing Time	Preheating Time	Pressing Time	Cooling Time	Top Heater Temperature	Bottom Heater Temperature	Pressure
KYDEX® XD	1 second	70-80 seconds	65-75 seconds	80-90 seconds	130°C - 150°C (266°F - 302°F)	82°C - 88°C (180°F - 190°F)	2 Bars (29 psi)
KYDEX® XDWG	1 second	120-140 seconds	85-95 seconds	110 seconds	130°C - 150°C (266°F - 302°F)	82°C - 88°C (180°F - 190°F)	2 Bars (29 psi)

Values above are for comparison only. For recommended conditions specific to your membrane press type, please contact Technical Service: 800.682.8758

SEKISUI SPI

ISO 9001 and 14001 Certified

Customer Service

6685 Low St, Bloomsburg, PA 17815 USA
Phone: 800.325.3133, +1.570.389.5810
Outside the US: +1.570.389.5814
Fax: 800.452.0155, +1.570.387.7786
Email: info@sekisui-spi.com

Technical Service

Phone: 800.682.8758
Fax: +1.570.387.8722
Outside the US: +1.570.387.6997
techservice@sekisui-spi.com

sekisui-spi.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Product not intended for use as a heat resistant surface. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.