

NEMA LD3 Comparison for KYDEX® 3D Laminates

INTRODUCTION

The National Electrical Manufacturers Association (NEMA) Standards have been adopted in the public interest and are designed to eliminate misunderstandings between the manufacturer and the purchaser of high-pressure decorative laminates (HPDL) and to assist the purchaser in selecting and obtaining the proper product for their particular needs. SEKISUI SPI submitted KYDEX® XD, XD03 and XDWG for evaluation.

		KYDEX® XD	KYDEX® XD03	KYDEX® XDWG
LD3.3	Light Resistance – xenon arc	No Effect	Severe Effect	No Effect
LD3.4	Cleanability Resistance (Sum of Scores)	9	9	14
LD3.4	Stain Resistance (Reagents 1 – 10)	No Effect	No Effect	No Effect Reagent 3 Severe Effect
LD3.4	Stain Resistance (Reagents 11 – 15)	No Effect	No Effect	No Effect
LD3.5	Boiling Water Resistance	Severe Effect	Severe Effect	No Effect
LD3.6.3	High Temperature Resistance (oil)	Moderate Effect	Moderate Effect	Moderate Effect
LD3.7.2	Linear Glass Scratch Resistance	<50g	<50g	<50g
LD3.7.3	Diamond Scratch Resistance	3	3	2
LD3.8	Ball Impact Resistance (mm)	>3000	>3000	>3000
LD3.9	Dart Impact Resistance (mm)	>1075	>1075	>875
LD3.10.2	Radiant Heat Resistance - Coil (sec)	46	46	43
LD3.10.3	Radiant Heat Resistance - Strip (sec)	47	47	51
LD3.11	Dimensional Change (MD)	0.26%	0.26%	1.05%
LD3.11	Dimensional Change (CMD)	0.39%	0.39%	0.67%
LD3.12	Dimensional Stability (MD)	0.07%	0.07%	0.08%
LD3.12	Dimensional Stability (CMD)	0.03%	0.03%	0.07%
LD3.13	Wear Resistance (cycles)	3700	3700	650
Misc.	ASTM E-84 Surface Burning Characteristics	Class 1/A	Class 1/A	Class 1/A



Customer Collaboration

6685 Low St, Bloomsburg, PA 17815 USA
 Phone: 800.325.3133, +1.570.389.5810
 Email: info@kydex.com

applab™

Phone: 800.682.8758
 Email: applab@kydex.com

kydex.com

Because we cannot anticipate or control the many different conditions under which this information and our products may be used, we do not guarantee the applicability of the accuracy of this information or the suitability of our products in any given situation. Users should conduct their own tests to determine the suitability of each product for their particular purposes. Data in the physical property table represents typical values and are to serve only as a guide for engineering design. Results are obtained from specimens under ideal laboratory conditions. Right to change physical properties as a result of technical progress is reserved. THE PRODUCTS DISCUSSED ARE SOLD WITHOUT WARRANTY OF MERCHANTABILITY OR FITNESS FOR A PARTICULAR USE, EITHER EXPRESSED OR IMPLIED, EXCEPT AS PROVIDED IN OUR STANDARD TERMS AND CONDITIONS OF SALE. Buyer assumes all responsibility for loss or damage arising from the handling and use of our products, whether done in accordance with directions or not. In no event shall the supplier or the manufacturer be liable for incidental or consequential damages. Also, statements concerning the possible use of our products are not intended as recommendations to use our products in the infringement of any patent. Consult local code and regulatory agencies for specific requirements regarding code compliance, transporting, processing, recycling and disposal of our product. Texture, product grade and other conditions may cause variations in appearance.

This information supersedes all previously published data.